

Proud Member and Participant of:

www.eastcoasterosion.com











Material and Performance Specification

ECS-2® Double Net Straw Rolled Erosion Control Product

Description:

Matrix:

The ECS-2® is made with uniformly distributed 100% agricultural straw and two polypropylene nets securely sewn together with degradable thread. The tightly compressed blankets are wrapped and include a product label, code and installation guide. The blankets are palletized for easy transportation. The ECS-2® has functional longevity of approximately 12 months, but will vary depending on soil and climatic conditions, and is suitable for slopes 2:1 or less and low to medium flow channels. The ECS-2® meets Type 2.D specification requirements established by the Erosion Control Technology Council (ECTC) and Federal Highway Administration's (FHWA) FP-03 Section 713.17.

IVIGETIA.				
	100% Straw			
Netting:	Туре		Net Color	
Top: Light	weight Photodegradable Polypropylene		Green	
Middle: None				
Bottom: Light	weight Photodegradable Polypropylene			
Net Opening:	Тор	Middle	Bottom	
	0.5" x 0.5"		0.5" x 0.5"	
Thread:	Туре	Color		
	Degradable Thread	White		
Roll Sizes:	Standard	"A" Size	Mega	
Width:	7.5 ft 2.3 m	3.75 ft 1.1 m	15 ft 4.6 m	
Length:	120 ft 36.6 m	240 ft 73.2 m	120 ft 36.6 m	
Weight <u>+</u> 10%:	53 lbs 24.0 kg	53 lbs 24.0 kg	106 lbs 48.1 kg	
Area:	100 yd ² 83.6 m ²	100 yd ² 83.6 m ²	200 yd ² 167.2 m ²	
#/Pallet:	20	9	16	

Index Value Properties*:					
Property	Test Method	T	Typical		
Mass/Unit Area	ASTM D6475	8.50 oz/yd ²	288.2 g/m2		
Thickness	ASTM D6525	0.32 in	8.13 mm		
Tensile Strength-MD	ASTM D6818	150 lb/ft	2.19 kN/m		
Elongation-MD	ASTM D6818	28 %			
Tensile Strength-TD	ASTM D6818	80 lb/ft	1.17 kN/m		
Elongation-TD	ASTM D6818	29.4 %			
Light Penetration	ASTM D6567	19 %			
Density / Specific Gravity	ASTM D792	N/A %			
Water Absorption	ASTM D1117	390 %			

^{*}May differ depending upon raw material variations

ope Performance De	esign Values*:			
Property	Test Method ASTM D6459		Value 0.01	
C-Factors				
Slope Length (L)	≤ 3:1	3:1-2:1	≥ 2:1	
< 50 ft (15 m)	0.014	0.077	N/A	
50 ft – 100 ft	0.048	0.084	N/A	
>100 ft (30 m)	0.086	0.125	N/A	

^{*}Large-Scale Results obtained by 3rd Party GAI Accredited Independent Laboratory

Test Method	Parameters	Results	
	50mm (2in) / hr-30 min	SLR**=5.84	
ECTC Method 2 Rainfall	100mm (4in) / hr-30 min	SLR**=6.87	
	150mm (6in) / hr-30 min	SLR**=8.09	
ECTC Method 3 Shear Resistance	Shear at .50 in soil loss	1.61 lb/ft ²	
ECTC Method 4 Germination To	p soil; Fescue; 21 day incub	ation 455 %	
*Bench scale tests should not be u	used for design purposes.		
**Soil Loss Ratio=Soil Loss Bare So	oil/Soil Loss with RECP=1/C-	Factor	

^{***}The preceding test data excerpts were reproduced with the permission of AASHTO, however, this does not constitute endorsement or approval of the product, material or device by AASHTO

Property	Test Method	Value			
Unvegetated Shear Stress	ASTM D 6460	2.05	lbs/ft ²	98.15	Pa
Unvegetated Velocity	ASTM D 6460	7.5	ft/s	2.29	m/s
Vegetated Shear Stress	NA	N/A	lbs/ft ²	N/A	Pa
Vegetated Velocity	NA	N/A	ft/s	N/A	m/s
Manning's N (Value Represe	ents a Range)		0.02	29	

^{*}Large-Scale Results obtained by 3rd Party GAI Accredited Independent Laboratory